

In compliance with the above invitation for proposals, and subject to all conditions thereof, the undersigned offers, and agrees if this bid be accepted within 30 days from the date of opening, to furnish any and all items at the price quoted opposite each item, F.O.B. as indicated.

BIDDER: _____

ADDRESS: _____

CITY, STATE, and ZIP: _____

PHONE: _____

TERMS: **Net 30** **DELIVERY:** _____

BY: _____ **TITLE:** _____

DATE: _____

Any question please contact
Dan Medina, Director of Maintenance
at 989-399-3773

SPECIFICATIONS

Aggregates

Aggregates shall consist of sound, tough, durable particles, free from adherent films of matter that would prevent thorough coating with the bituminous material. The percentage of wear shall not be greater than 45 percent when tested in accordance with ASTM C-131.

Aggregates shall contain 100 percent having at least one fractured face.

Sampling and Testing

ASTM D75 shall be used in sampling the aggregate. The Contractor shall furnish documentation to the Engineer, at the time of bid confirming that the aggregate meets both AWI and L.A. Abrasion specification requirements.

Sources of Aggregates

Sources of aggregates shall be selected well in advance of the time the materials are required on the work. When the aggregates are obtained from a previously approved source of an existing source producing aggregates that have a satisfactory service submitted 10 days prior to the start of construction. The Engineer will make an inspection of the producer's operation. Approval of the source of aggregate does not relieve the Contractor in any way of the responsibility for delivery at the job site of aggregates that meet the requirements specified herein.

Samples of Aggregates

Saginaw County Road Commission shall take samples of aggregate during the time of delivery. All samples taken will be required to meet the following requirements:

Gradation Report

Product: CS-2

<i>Sieve Designation</i>	Specification
<i>1/2" (12.5mm)</i>	100.0
<i>3/8" (9.5mm)</i>	85-100
<i>1/4" (6.7mm)</i>	0
<i>#4 (4.75mm)</i>	10-30
<i>#8 (2.36mm)</i>	0-10
<i>#200 (75um)</i>	0.3

Detail Gradation Statistical Summary Report

Product: 29A Limestone

Sieve/Test	Specification
1/2" (12.5mm)	100-100
3/8" (9.5mm)	90-100
#4 (4.75mm)	10-30
#8 (2.36mm)	0-10
#200 (75um)	0-3
Pan	

